



Survey of the occurrence of 1,6-hexanediol diglycidyl ether in food contact materials A LOUS 2012 - 2015 follow - up project

Pedersen, Gitte Alsing; Cederberg, Tommy Licht

Publication date:
2014

Document Version
Publisher's PDF, also known as Version of record

[Link back to DTU Orbit](#)

Citation (APA):

Pedersen, G. A., & Cederberg, T. L. (Eds.) (2014). *Survey of the occurrence of 1,6-hexanediol diglycidyl ether in food contact materials: A LOUS 2012 - 2015 follow - up project*. Danish Ministry of the Environment. Miljøprojekter Vol. 2014 No. 1583 <http://mst.dk/service/publikationer/publikationsarkiv/2014/jul/survey-of-the-occurrence-of-16-hexanediol-diglycidyl-ether-in-food-contact-materials/>

General rights

Copyright and moral rights for the publications made accessible in the public portal are retained by the authors and/or other copyright owners and it is a condition of accessing publications that users recognise and abide by the legal requirements associated with these rights.

- Users may download and print one copy of any publication from the public portal for the purpose of private study or research.
- You may not further distribute the material or use it for any profit-making activity or commercial gain
- You may freely distribute the URL identifying the publication in the public portal

If you believe that this document breaches copyright please contact us providing details, and we will remove access to the work immediately and investigate your claim.



Danish Ministry of the Environment
Environmental Protection Agency

Survey of the occurrence of 1,6- hexanediol diglycidyl ether in food contact materials

A LOUS 2012-2015 follow-up project

Environmental project no. 1583, 2014

Title:

Survey of the occurrence of
1,6-hexanediol diglycidyl ether
in food contact materials

Editing:

National Food Institute, Technical University of Denmark
Gitte Alsing Pedersen
Tommy Licht Cederberg

Published by:

The Danish Environmental Protection Agency
Strandgade 29
1401 Copenhagen K
Denmark
www.mst.dk/english

Year:

2014

ISBN no.

978-87-93178-71-7

Disclaimer:

When the occasion arises, the Danish Environmental Protection Agency will publish reports and papers concerning research and development projects within the environmental sector, financed by study grants provided by the Danish Environmental Protection Agency. It should be noted that such publications do not necessarily reflect the position or opinion of the Danish Environmental Protection Agency.

However, publication does indicate that, in the opinion of the Danish Environmental Protection Agency, the content represents an important contribution to the debate surrounding Danish environmental policy.

Sources must be acknowledged.

Contents

Preface	4
Summary and conclusion	5
Sammenfatning og konklusion	6
1. Introduction to the substance	7
1.1 Chemical name, structure and properties.....	7
1.2 Function of the substance for the main application areas	8
2. Information search strategy	9
2.1 Scientific literature and patents	9
2.2 International and national legislation regarding food contact materials.....	10
2.3 Inventory lists from industry organisations and governmental institutions	10
2.4 Databases on the use of substances in products in Denmark, in the Nordic countries and in Europe	10
2.5 Informal contacts to relevant Danish companies.....	10
3. Regulatory framework.....	11
3.1 EU regulation of food contact materials	11
3.2 National regulations and recommendations on food contact materials	11
4. Occurrence in food contact materials	13
4.1 Occurrence on regulations, recommendations and inventory lists	13
4.2 Industry information on the use of the substance.....	13
4.3 Registration in databases	14
4.4 Information search in scientific literature and databases.....	14
5. Overall findings and conclusions	16
5.1 Main findings	16
5.2 Conclusions	16
References	17

Preface

The Danish Environmental Protection Agency (EPA) performs surveys in the period 2012-2015 of all 40 substances and substance groups on the List of Undesirable Substances (LOUS). The surveys include collection of available information on the use and occurrence of the substances, internationally and in Denmark, information on environmental and health effects, on alternatives to the substances, on existing regulation, on monitoring and exposure and information regarding ongoing activities under REACH among others.

The Danish EPA will on the basis of the surveys assess the need for any further regulation, substitution/phase out, classification and labelling, improved waste management, development of new knowledge or increased dissemination of information.

The initial survey of 1,6-hexanediol diglycidyl ether indicated a possible use of the substance in materials and articles intended to come into contact with food. The aim of this project is to explore this information further and if confirmed, in which types of materials the substance may be found. The relevance of a follow-up study with chemical analyses of relevant types of food contact materials sampled in Denmark will be based on the results of this project.

The preparation of this report has been supervised by a reference group consisting of:

Lea Stine Tobiassen, Danish Environmental Protection Agency

Mette Holm, Danish Veterinary and Food Administration

Gitte Alsing Pedersen, National Food Institute, Technical University of Denmark

Tommy Licht Cederberg, National Food Institute, Technical University of Denmark

Summary and conclusion

Based on information retrieved in an initial survey of 1,6-hexanediol diglycidyl ether within the LOUS-project, it cannot be excluded that the substance could be used in materials and articles intended to come into contact with food. The aim of this project was defined to be an exploration of the possible use of the substance in food contact materials.

The immediate information available on the use of the substance in food contact materials is limited. The information search strategy has included a broad spectrum of information sources: scientific literature; patent search; inventory lists from industry organisations and governmental institutions; international and national legislation regarding food contact materials; databases on the use of substances in products in Denmark, the Nordic countries and in Europe as well as informal contacts to relevant Danish companies.

All food contact materials (FCM's) are regulated by the framework EU regulation (EC) No 1935/2004. Moreover, a specific measure exists for materials and articles of plastics intended for food contact (Regulation (EU) No 10/2011). The substance 1,6-hexanediol diglycidyl ether is not on the positive list in the EU regulation for plastic food contact materials and articles. It may therefore not be used legally in these materials on the Danish market.

The substance is not listed on the US Food and Drug Administration (FDA) regulation lists (175 and 176) of indirect additives used in food contact materials or on the inventory list of printing inks prepared by an EFSA Scientific Cooperation (ESCO) Working Group. However; it is listed as a permitted additive and is on the list of solvent in the national regulation in Switzerland for printing inks. Also, the substance is listed on the inventory industry list of the European Trade Association for printing ink makers, EuPIA.

From searching in scientific literature and databases it was not possible to find information on actual use of the substance within food contact materials applications and the European Council of Paint and Printing Inks informed that the substance is not used for lacquers and inks for metal packaging for food. In patent applications the substance is mentioned in relation to coatings for drinking water tanks, paper wet strength agents, electronic packaging materials and coatings of medical devices.

In a correspondence a Danish company reported a possible use of the substance in preparations used for coatings of drinking water tanks and pipelines. Thus the use of 1,6-hexanediol diglycidyl ether for this type of application cannot be excluded. No information was found with regards to release of residual monomers of 1,6-hexanediol diglycidyl ether from epoxy coatings. To the extent that 1,6-hexanediol diglycidyl monomer residues are migrating from epoxy coatings it will be released to the water phase as it is soluble in water.

Except for water tanks no specific description of 1,6-hexanedioldiglycidylether in relation to food contact materials was found in this survey.

Sammenfatning og konklusion

I en tidligere kortlægning af 1,6-hexandiolglycidylether i forbindelse med LOUS-projektet kunne det ikke udelukkes, at stoffet bliver brugt i materialer, der kan komme i kontakt med fødevarer. Formålet med dette projekt blev defineret til at være en undersøgelse af den mulige brug af stoffet i materialer, der kommer i forbindelse med fødevarer.

Der er begrænset viden om brugen af stoffet i fødevarekontaktmaterialer og strategien for informationssøgningen har inkluderet et bredt spektrum af informationskilder: Videnskabelig litteratur, patentsøgninger, fortegnelser fra brancheorganisationer og offentlige institutioner, international og national lovgivning om fødevarekontaktmaterialer, produktregistre i Danmark, de nordiske lande og Europa, og uformelle kontakter til relevante danske virksomheder.

Stoffet 1,6-hexandiolglycidylether er ikke på EU-positivlisten for fødevarekontaktmaterialer af plast. Det er derfor ikke lovligt at bruge i artikler eller materialer på det danske marked.

Stoffet er heller ikke på US FDA's positivlister vedrørende indirekte additiver til brug i fødevarekontaktmaterialer eller en liste med trykfarver udarbejdet af en EFSA videnskabelig arbejdsgruppe (ESCO). Derimod optræder stoffet på den schweiziske stofliste for trykfarver, både som additiv og solvent, og på stoflisterne fra den europæiske brancheorganisation for trykfarver, EUPIA, henholdsvis som additiv og hærdende monomer.

Ved søgning i den videnskabelige litteratur og øvrige databaser blev der ikke fundet informationerne om brugen af 1,6-hexandiolglycidylether i fødevarekontaktmaterialer.

I patentansøgninger er stoffet nævnt i forbindelse med drikkevandstanke, vådstyrkemidler til papir, emballage til elektronik og overfladebehandling af medicinsk udstyr.

Ved en forespørgsel har en dansk virksomhed oplyst, at stoffet kan finde anvendelse ved epoxy coatings i drikkevandstanke og -rør, så anvendelse af 1,6-hexandiolglycidylether til disse formål kan derfor ikke udelukkes. Der er ikke blevet fundet oplysninger om afgivelse af restmonomere af 1,6-hexandiolglycidylether fra epoxy coatings. I det omfang at restmonomere migrerer fra epoxy coatings vil det blive tilgængeligt i vandfasen, da stoffet er vandopløseligt.

Bortset fra drikkevandstanke er der i denne undersøgelse ikke fundet specifik anvendelse for 1,6-hexandiolglycidylether i relation til fødevarekontaktmaterialer.

1. Introduction to the substance

A general survey of 1,6-hexanediol diglycidyl ether has previously been conducted. The survey describes the chemistry, manufacture, use and human health aspects of the substance. For an overview of chemical names, structure, properties, manufacture and main application areas of 1,6-hexanediol diglycidyl ether these information's are listed from the survey in this chapter (Hansen, et al., 2013).

1.1 Chemical name, structure and properties

1,6-hexanediol diglycidyl ether is an ether compound connected to ethylene oxide (oxirane) at both ends.

CAS No: 16096-31-4

EC No: 240-260-4

Relevant synonyms for 1,6-hexanediol diglycidyl ether include:

- hexane,1,6-bis(2,3-epoxypropoxy)
- 1,6-bis(2,3-epoxypropoxy)hexane
- 1,6-bis(glycidyloxy)hexane
- 1,6-hexamethylenediol diglycidyl ether
- hexamethylene diglycidyl ether
- hexamethylene glycol diglycidyl ether
- hexanediol diglycidyl ether
- HDDGE

Structural formula:




FIGURE 1
STRUCTURAL FORMULA OF 1,6-HEXANEDIOL DIGLYCIDYL ETHER

The substance is a colourless and odourless liquid at room temperature and standard atmospheric pressure with the following physico-chemical properties:

Molecular Formula: $C_{12}H_{22}O_4$

Molecular weight: 230.3

Melting point: -23.7°C

Boiling point: 328.7°C

Flash point: $120-179^{\circ}\text{C}$

Density: 1.076 g/cm^3

Log Pow: 0.82 at 20 °C

Vapour pressure: 0.002 mg Hg (very low volatility)

The water solubility was in the general survey listed as insoluble in water but the substance is registered in REACH as very soluble under ambient conditions with a solubility of 11.9 g/L (ECHA, 2014). In the SciFinder chemical database (see chapter 3) the substance is reported to have solubility in water of 2.5 g/L at 25 C and pH 1-10. This value has been generated by chemical modelling software.

CAS No	EC No	Substance name	Registered, tonnage band (t/y)
16096-31-4	240-260-4	1,6-bis(2,3-epoxypropoxy)hexane	1,000-10,000

TABLE 1

REGISTERED TONNAGE OF 1,6-HEXANEDIOL DIGLYCIDYL ETHER AT THE EUROPEAN CHEMICALS AGENCY

1.2 Function of the substance for the main application areas

The dominant function of the substance is as a reactive diluent in particular related to epoxy systems. A diluent is an organic liquid added to resin formulations, with no solvent power, to reduce viscosity and to ease flow movement or to improve consistency and applicability.

2. Information search strategy

The general survey (Hansen et al., 2013) found very little information on 1,6-hexanediol diglycidyl ether. Most applications appears to be in the building sector e.g. plasters, fillers, sealants, coatings and paints. However, its use in materials intended to come into contact with food (FCM) could not be excluded. Initial and preliminary information search in the scientific literature and other published information sources in this survey revealed no clear answers concerning the possible use of 1,6-hexanediol diglycidyl ether in FCM.

The final search strategy for information of the occurrence of 1,6-hexanediol diglycidyl ether in food contact materials has included a broad spectrum of information sources:

- Scientific literature
- Patent search
- International and national legislation regarding food contact materials
- Inventory lists from industry organisations and governmental institutions
- Databases on the use of substances in products in Denmark, in the Nordic countries and in Europe
- Informal contacts to relevant Danish companies

2.1 Scientific literature and patents

The search has been performed in the following databases:

- FindIt: DTU Library's general electronic information search tool. The search includes approx. 170 million references - mainly scientific articles, e-books, conference papers and journals in the technical-scientific and related disciplines.
- Web of Science: Web of Science consists of several databases containing information gathered from scientific journals in all areas of research.
 - Science Citation Index Expanded (1900-present)
 - Social Sciences Citation Index (1956-present)
 - Arts & Humanities Citation Index (1975-present)
 - Conference Proceedings Citation Index - Science (1990-present)
 - Conference Proceedings Citation Index - Social Science and Humanities (1990-present)
- SciFinder: provides access to a wide diversity of research from many scientific disciplines. It includes the Chemical Abstract Service database which is created and maintained by scientists, and have references from over 9,500 currently published journals and patent information from more than 50 active patent issuing authorities. The coverage is chemistry incl. patents, as well as topics like life sciences including biochemistry, biology, pharmacology, medicine, and related disciplines. In addition SciFinder contains the world's largest collection of organic and inorganic substance chemistry information.

2.2 International and national legislation regarding food contact materials

The search strategy has included a search into positive lists of substances in international and national legislations on food contact materials, e.g. the EU positive list on plastic materials used for Food Contact Materials. The particular regulations are listed in chapter 3.

2.3 Inventory lists from industry organisations and governmental institutions

Inventory lists by the European Food Safety Authority, EFSA

The Executive Director of EFSA did in 2010 initiate an EFSA Scientific Cooperation (ESCO) working Group in order to set up inventory lists for substances used for preparation of non-plastic food contact materials. The list is compiled based on information in Member States, Switzerland and Norway. The list includes varnishes and coatings, colorants, wood and cork, paper and paperboard, printing inks, rubbers and silicones (EFSA, 2011).

Industry inventory lists and guidelines on food contact materials

The European Trade Association for printing ink makers, EuPIA, has published guidance documents on packaging inks to their member companies (EuPIA, 2011). EuPIA has in the absence of specific EU legislation for food packaging inks developed a guideline for selection of raw materials for printing inks intended to be applied on the non-food contact surface of food packaging. As Part of the guideline an inventory list of packaging ink substances used for the non-food contact surface of food contact materials is given (EuPIA, 2013).

2.4 Databases on the use of substances in products in Denmark, in the Nordic countries and in Europe

Danish Product Registry: the Product Registry at the Danish Working Environment Authority registers both individual substances and mixtures of substances (preparations). Danish companies have a duty to notify hazardous chemical products to the Product Registry. The notification duty applies to companies that produce, import or change the trade name of hazardous chemical products in quantities exceeding 100 kg per year.

SPIN - Substances in Preparations In the Nordic countries - contains information on chemical substances from each of the Nordic product registers. Information available in SPIN: substances in preparations on the Nordic market; total use – volume in tons; industrial use; use category – product types; exposure potential for primary recipients.

REACH registrations: Database of Industry registration dossiers according to the REACH regulation, including information on the uses of chemical substances throughout Europe. REACH registers individual substances only.

2.5 Informal contacts to relevant Danish companies

The European Trade Association for printing inks, EuPIA, as well as the Danish Coatings and Adhesives Association were personally contacted for information on the potential use of 2,5-di-tert-butylhydroquinone in materials intended for food contact. Moreover some Danish producers of printing inks and adhesives for food contact materials were contacted to obtain specific information on the use of the given substance in Danish productions of these materials.

3. Regulatory framework

3.1 EU regulation of food contact materials

In EU food contact materials (FCM) are regulated by the Framework regulation no 1935/2004 (EU, 2004). The requirements in regulation no 1935/2004, covered by article 3, are crucial for ensuring food safety. These general requirements state that FCM shall, under normal and foreseeable conditions of use, not transfer their constituents into foodstuffs in quantities, which could:

- Endanger human health
- Bring about an unacceptable change in the composition of the foodstuffs
- Bring about deterioration in the organoleptic characteristics thereof

This regulation applies to all FCM, which in their finished state are:

- Intended to be brought into contact with food
- Already brought into contact with food and are intended for that purpose
- Can reasonably be expected to be brought into contact with food or to transfer their constituents to food under normal or foreseeable conditions of use

In addition to the frame work regulation, food contact materials made of plastic are moreover covered by a specific regulation given by EU no 10/2011 and amendments (EU, 2011). The scope includes plastic coatings and gaskets on metal lids and plastic layers in multi-material multilayer FCMs. The regulation covers a positive list of monomers and other starting substances. These lists include for some substances restrictions on their migration (Specific Migration Limits, SML), the concentration in the FCM (Qm), or their purity or permitted use (e.g. not permitted for plastics in contact with fatty foods). Regulation 10/2011 requires that a declaration of compliance (DoC) is supplied for plastic materials and articles at the non-retail stages. The information required to be supplied in the DoC is set out in an Annex to the Regulation.

Where a specific measure has not yet been introduced for a given FCM, the substance must comply with the general provisions of the Framework Regulation 1935/2004. Compliance with regulation 1935/2004 shall be based on risk assessments of the chemicals used in the composition of the materials, including evaluation of possible migration of the chemicals into food. In addition to the harmonised legislation in Europe, some countries have national legislation in specific areas.

3.2 National regulations and recommendations on food contact materials

Swiss Regulation on printing inks

In Switzerland a regulation for printing inks was issued in 2010. On the basis of the inventory list of substances given by The European Trade Association for printing ink makers (EuPIA) and Council of Europe, the list has been regularly revised and a complete list of substances in use is provided (FDHA, 2011). According to the regulation, packaging inks may only be manufactured from substances in the regulation. The lists of substances are divided into a part A and part B. Part A contains evaluated substances subjects to the requirements set out therein, intended to be used in

the manufacture of food contact materials. Substances in part B have not been subjected to any official recognised scientific testing. The use of these substances is permitted if no transfer of the substances to food or food simulants can be detected.

The substances in Part B of the lists must not be detectable in a migration test in the lowest possible concentration at which a substance may be detected using a valid method of analysis. The detection limit depends on the composition of the substance; this limit, expressed as a concentration, must never exceed 0.01 mg/kg of food or food simulants (including the analytical tolerance). For substances that can be allocated to a group of compounds with similar toxicology or similar basic structure (e.g. isomers), this limit value applies to the sum of the concentrations of the substances.

German recommendations and regulations on food contact materials

In addition to EU regulations on food contact materials the German Federal Institute for Risk Assessment, Bundesinstitut für Risikobewertung (BfR) have recommendations on materials and substances for which there is no harmonised EU regulation (BfR, 2013). In the field of plastics these substances are aids to polymerisation as catalysts and initiators, as well as polymerisation production aids like e.g. emulsifiers, which are needed in the manufacturing process. The database moreover includes recommendations for other materials than plastics as e.g. paper and board, silicones and rubber. The BfR Recommendations on Food Contact Materials are not legal norms.

Moreover, a national legislation on printing inks is under preparation in Germany (Nordic Council of Ministers, 2012). The draft regulation will include a list of substances which are approved (due to evaluations by EFSA, JECFA and BfR) for use in printing ink formulations for food contact materials. The starting point for this is the Swiss regulation on printing inks. In addition to this, chemicals which have not been risk assessed are listed but are not included in the legislation. The non-regulated substances may be used if the migration is not detectable (detection limit of 10 microgram per kg food) and the substances are not classified as either carcinogenic, mutagenic or reprotoxic. Toxicological risk assessment and an authorization procedure for chemicals used in printing ink will be a part of the proposed activity in Germany.

National regulations on printing inks in the Nordic countries

None of the Nordic countries have additional national legislation on printing inks and coatings. However, in Denmark, Finland and Norway declaration of compliance, DoC, for all type of FCM including packaging inks is requested.

Danish regulation on materials and articles in contact with drinking water

In Denmark drinking water is regulated by a new regulation on authorisation of materials in contact with drinking water (Ministry of Climate, Energy and Building, 2013a and b). This regulation covers materials, including coatings, in contact with drinking in the permanent installations until the tapping. According to the regulation the materials must not have health hazardous effect. Materials that are not part of the permanent installations for drinking water, i.e. after the tap, are covered by the EU regulations for food contact materials including the Framework regulation no 1935/2004 (EU, 2004) and EU regulation no 10/2011 for materials made of plastic (EU, 2011).

Regulation on Food contact materials by US Food and Drug Administration, FDA

In US, food contact materials are regulated by the US Food and Drug Administration, FDA, by the regulation Code of Federal Legislation (CFR) 21 on Indirect Food Additive Substances that may come into contact with food as part of packaging or processing equipment (US FDA, 2013). The regulation includes the following lists: 21 CFR 175 Indirect food additives: Adhesives and components of coatings, 21 CFR 176 Indirect food additives: Paper and paperboard components, 21 CFR 177 Indirect food additives: Polymers.

4. Occurrence in food contact materials

4.1 Occurrence on regulations, recommendations and inventory lists

EU regulation on materials and articles of plastic for food contact EU 10/2011.

The substance is not on the European Union list of authorised monomers and other starting substances for food contact materials in the regulation on plastic materials and articles intended to come into contact with food (EU, 2011). The substance is therefore not legally to be used in food contact materials of plastic on the European market.

Materials under the German Recommendations

The substance was not found on the list of substances in the database of the German regulation of Food contact materials.

Swiss Regulation on printing inks

1,6-hexandiol diglycidyl ether is on the list of permitted additives in printing inks in part A and on the list of solvents in part B of the regulation. In both lists it is marked as being an energy curing monomer (monomers which react chemically to form the binder of the printing ink).

As mentioned in chapter 3.2 substances on part B have not been subjected to any officially recognised scientific testing (such as that of the scientific committee of the EFSA). The use of these substances is permitted if no transfer of these substances to food or food simulants can be detected. The relevant proof can be provided by means of a "worst case" calculation or by a practical experiment.

US Food and Drug Administration FDA

1,6-hexandiol diglycidyl ether is not found on FDA list (175 and 176) of indirect additives used in food contact substances. The substance is thus not permitted in adhesives and coatings or in paper and paperboard in the US.

EuPIA inventory list

The substance, 1,6-hexanediol diglycidyl ether, is found on the EuPIA inventory lists of printing ink raw materials applied to the non-food contact of food packaging as "substances used as additives or ingredients of additive preparations" and "energy curing monomers" (EuPIA, 2013).

EFSA

The substance was not found on the EFSA Scientific Cooperation (ESCO) inventory list of substances for food contact material of non-plastic (EFSA, 2011). The list includes substances on printing inks, coatings, paper and board, rubber and wood for food contact.

4.2 Industry information on the use of the substance

The European Council of Paint and Printing Inks, CEPE, confirmed that the substance is not used for lacquers and inks for metal packaging for food. A Danish company in the paint and lacquers

industry has reported that 1,6-hexanediol diglycidyl ether is used as an epoxy diluent as a part of a raw material used by them. Epoxy paints are used in chemical containers, various pipelines and drinking water tanks. The company use 1,6-hexanediol diglycidyl ether in a quantity of 800 kg/year in Denmark (personal communication to the Danish Coatings and Adhesives Association, 2013).

4.3 Registration in databases

The substance belongs to the European inventory of existing commercial chemical substances (EINECS) as it is recorded as being commercially available in the EU from 1 January 1971 to 18 September 1981. It was therefore registered under the REACH regulation as a phase-in substance in November 2010.

In Table 2 the reported use of the substance in various product categories is listed. The uses in consumer's products are in adhesives, sealants, coatings, fillers and plasters.

Chemical product category:

PC 1: Adhesives, Sealants

PC 9a: Coatings and paints, thinners, paint removes

PC 9b: Fillers, putties, plasters, modelling clay

TABLE 2
CHEMICAL PRODUCT CATEGORY IN REACH REGISTERED BY COMPANIES

In the Danish product register substance is in 2013 registered to be used in 12 technical categories in 64 tonnes per year. The use areas was paint and lacquers, binders, flooring materials, construction materials, surfactants, fillers and other applications (listed in decreasing registered consumption). It is registered to be used in 84 different products; however no information was given if these applications include food contact materials.

In the database of the Nordic Product Register, SPIN, the substance is mainly registered to be used for construction materials; adhesives and binding agents; paint, lacquers and varnishes; fillers; surface treatment and others. In Denmark the registered use in 2011 was 41 tonnes. However; no information was found if the substance is used for food contact materials.

4.4 Information search in scientific literature and databases

In the scientific literature published information of 1,6-hexanediol diglycidyl ether is found concerning chemical structure, chemical reactions in relation to polymers and epoxy resins. In most cases the publications and other information's are directed against the use in products already mentioned as the main application areas such as adhesives, coatings, paints used in construction and building industries.

One recent scientific paper describes the synthesis of a new UV-curable prepolymer – hexanediol diglycidyl ether diacrylate – and its cured film property (Huang et al., 2011). UV-cured films have industrial applications as protective coatings, printing ink and adhesives. Generally bisphenyl A diglycidyl ether diacrylate is used as prepolymer but other prepolymers can have better producing and mechanical and properties.

A thirteen years old scientific paper discusses the different UV-curable formulations suitable for printing on plastics substrates (Lombardi et al., 2000)

No direct reference to the use in food contact materials was found.

Patents

In several patents the substance 1,6-hexanediol diglycidyl ether is mentioned. In most cases 1,6-hexanediol diglycidyl ether is listed as one of many possible chemical reactants which can be a part of the chemical substances used for synthesis of the product in the patent application. The found patents cover the following application areas:

- Coatings for concrete drinking water pools (Ishida et al., 1993)
- Paper wet strength agent (product which provide strength to the paper when it is wetted (Chen, 2013; Pei and Dongping, 2010)
- Printing ink (Jego et al., 2003; Furukawa, 1998)
- Electronic packaging material (Deng, 2013)
- Coatings for medical devices (Hsu et al., 2001; Bauer and Juergen, 1993)

With the exception of coatings for drinking water tanks no direct reference to the use in food contact materials was found.

5. Overall findings and conclusions

5.1 Main findings

The substance 1,6-hexanediol diglycidyl ether is not on the positive list in the EU regulation for plastic food contact materials and articles. It may therefore not be used legally in these materials on the Danish market. Nor is the substance on the US FDA regulation lists (CFR 175 and 176) of indirect additives used in food contact materials or the ESCO inventory list for printing ink.

However; it is listed as a permitted additive and a solvent in the national regulation in Switzerland for printing inks as well as on the inventory industry list of the European Trade Association for printing ink makers, EuPIA.

From searching in scientific literature and databases it was not possible to find information on actual use of the substance within food contact materials applications. A main application is within coating and paints and a possible use is for coating of tanks for drinking water tanks and pipelines, as reported by a Danish company. Application in printing ink is reported in a scientific article and in two patents. This is in line with the listing of the substance in the Switzerland regulation and the inventory list of EuPIA.

In patent applications the substance is also mentioned in relation to drinking water tanks, paper wet strength agents, electronic packaging materials and coatings of medical devices. In the last three applications no specific description was found in relation to food contact materials.

5.2 Conclusions

The result of the survey indicates that the substance probably is used in coatings of drinking water tanks and pipelines. No information was found with regards to release of residual monomers of 1,6-hexanediol diglycidyl ether from cured epoxy coatings. To the extent that monomer residues of 1,6-hexanediol diglycidyl is migrating from epoxy coatings it will be released to the water phase as it is soluble in water.

Except for drinking water tanks no specific description of 1,6-hexanedioldiglycidylether in relation to food contact materials was found in this survey.

References

Bauer, Kurt H., and Juergen Betzing. 1993. *Preparation and use of biodegradable crosslinked polysaccharides*. Patent DE4209160A1, filed 1993, and issued 09/30.

BfR, 2013. Recommendations on Food Contact Materials Database BfR. Retrieved April 30, 2014, from http://www.bfr.bund.de/en/database_bfr_recommendations_on_food_contact_materials_formerly_plastics_recommendations_-1711.html

Chen, Dongping. 2013. *A paper wet strength agent and preparation method thereof*. Patent CN103362032A, filed 2013, and issued 10/23.

Deng, Xiaolan, Anlian Xu, and Yunbo Huang. 2013. *Modified filler-containing heat-conducting electronic packaging material*. Patent CN103074022A, filed 2013, and issued 05/01.

DEPA, 2011. List of Undesirable Substances. 2009. Orientering fra Miljøstyrelsen. Environmental Review No. 3, 2011.

ECHA, 2014. Registered data on 1,6-hexanediol diglycidylether at European Chemical Agency. Retrieved April 20, 2014. http://apps.echa.europa.eu/registered/data/dossiers/DISS-975e8b6d-e9f5-079f-e044-00144f67d031/AGGR-5a65eec2-035d-4bd8-ac41-95e6c02aa6d5_DISS-975e8b6d-e9f5-079f-e044-00144f67d031.html#ADMIN_DATA

EFSA, 2011. Report of ESCO WG on non-plastic Food Contact Materials. Question number: EFSA-Q-2009-00980. European Food Safety Authority, 2011.

EU, 2004. Regulation (EC) No 1935/2004 of the European Parliament and of the Council, of 27 October 2004 on materials and articles intended to come into contact with food and repealing Directives 80/590/EEC and 89/109/EEC.

EU, 2011. Commission regulation (EU) No 10/2011 of 14 January 2011 on plastic materials and articles intended to come into contact with food.

EuPIA, 2011. EuPIA Guideline on Printing Inks applied to the non-food contact surface of food packaging materials and articles. November 2011 – corrigendum July 2012. Retrieved April 30, 2014, from http://www.eupia.org/uploads/tx_edm/2011-11-14_EuPIA_Guideline_for_Food_Packaging_Inks.pdf

EuPIA, 2013. Inventory list – version December 2013. Comprising of packaging ink raw materials applied to the non-food contact surface of food packaging. European Printing Ink Association. Retrieved April 30, 2014, from http://www.eupia.org/uploads/tx_edm/131231_Inventory_List.pdf

FDHA, 2011. Swiss Ordinance of the Federal Department of Home Affairs (FDHA) on Materials and Articles (817.023.21). Section 8b: Packaging Inks, into force from April 2010.

- Furukawa, Akira. 1998. *Ink-jet printing sheets for water-based ink*. Patent JP10157282A, filed 1998, and issued 06/16.
- Hansen, Erik, Frans Møller Christensen, Jesper Kjølholt, Christian Nyander Jeppesen og Carsten Lassen (2013). Survey of 1,6-hexandiol diglycidyl ether. Part of the LOUS-review. Environmental Review No. 1472. The Danish Environmental Protection Agency, Copenhagen, Denmark. ISBN 978-87-93026-00-1.
- Huang, Biwu, Chen Weiqing, Yang Zhihong, Jiang Ankun, Weng Zixiang. 2011. Synthesis of a Novel UV-curable Prepolymer Hexanediol Diglycidyl Ether Diacrylate and Its Cured Film Tensile Property. *J. Wuhan Univ. Technol. -Mat. Sci. Edit.* 26, 4-9.
- Hsu, Li-chien, Can B. Hu, and Sun-de Tong. 2001. *Universal biocompatible coating platform for medical devices*. Patent WO2001008718A1, filed 2001, and issued 02/08.
- Jego, Elodie, Denis Perisse, and Pierre Cocagne. 2003. *Solvent-free, liquid ink with stable viscosity for ink-jet printing*. Patent WO2003011990A2, filed 2003, and issued 02/13.
- Ishida, Yoshio, Hiroshi Iizuka and Toru Tomoshige, 1993. *Two-component epoxy resin compositions*. Patent US005229438A, filed Nov. 1990, issued July 20, 1993.
- Jego, Elodie, Denis Perisse, and Pierre Cocagne. 2003. *Solvent-free, liquid ink with stable viscosity for ink-jet printing*. Patent WO2003011990A2, filed 2003, and issued 02/13.
- Lombardi, V., M. Sangermano, A. Osella, A. Priola, and A. Bigogno. 2000. Characterization of UV-curable inks and varnishes for flexo-printing on plastic films. *FATIPEC Congress 25th* : 141-59.
- Nordic Council of Ministers, 2012. Food contact materials: Printing Inks. Check lists for compliance in industry and trade and control by food inspection. Tema Nord 2012:521. ISBN 978-92-893-2348-2. www.norden.org/en/publications.
- Ministry of Climate, Energy and Building, 2013a. Bekendtgørelse om udstedelse af godkendelse for byggevarer i kontakt med drikkevand. Bekendtgørelse nr. 31 af 21-01-2013.
- Ministry of Climate, Energy and Building, 2013b. Bekendtgørelse om ændring af bekendtgørelse om udstedelse af godkendelser for byggevarer i kontakt med drikkevand. Bekendtgørelse nr 1259, 5/11/2013.
- Pei, Jindong, and Dongping Chen. 2010. *Reactive thinner-modified paper wet strength agent, and preparation method thereof*. Patent CN101929109A, filed 2010, and issued 12/29.
- US FDA, 2013. Code of Federal Regulations Title 21. List of Indirect Additives used in food contact materials. US Food and Drug Administration. Last updated: 06/01/2013. <http://www.accessdata.fda.gov/scripts/cdrh/cfdocs/cfcfr/cfrsearch.cfm>.

Survey of the occurrence of 1,6-hexanediol diglycidyl ether in food contact materials

This project is a survey of the occurrence of 1,6-hexanediol diglycidyl ether (HDDGE) specifically in food contact material on the Danish market.

The project is following up on a previous survey under the Danish EPA's LOUS-review (Environmental Project no. 1477).

This survey clarifies that HDDGE is listed on an inventory for possible use in printing inks food contact materials, but that is not used by European producers and importers. The substance is not allowed for use in plastic materials for food contact. One Danish company reported a possible use of HDDGE in coating of drinking tanks and pipelines. This is the only use of HDDGE confirmed in relation to food contact materials in Denmark.



Danish Ministry of the Environment
Environmental Protection Agency

Strandgade 29
1401 Copenhagen K, Denmark
Tel.: (+45) 72 54 40 00

www.mst.dk